



# TECHNICAL BULLETIN

Raybo Chemical Company

TELEPHONE: 304-525-5171

## RAYBO 26 - Slikit

### Scratch Resistance

REFERENCE	FEATURES	SYSTEM	COMMENTS	USAGE (%)	REFERENCE
	Scratch Resistant Additive (Air Dry)	Solvent	Can Be Used In Low Temperature Bake Systems	0.5 – 2.0% of Total Vehicle Solids	

#### PERFORMANCE

RAYBO 26 is intended for use in air dry systems as a scratch resistance additive. It can also be used in bake systems which will not be subjected to temperatures in excess of 200°F.

RAYBO 26 will not contribute to pinholing or intercoat adhesion loss.

RAYBO 26 becomes a part of the coating film and contributes to a low coefficient of friction for the coating surface.

#### ADVANTAGES

- Can be used in air dry and low bake systems
- Does not contribute to intercoat adhesion loss
- Fluid for ease of addition

#### RECOMMENDATIONS

For scratch and mar resistance – 0.5-2.0% of Total Vehicle Solids  
Can be added at any time including post addition. Use with lacquer systems or oxygenated solvents not recommended.

#### PHYSICAL DATA\*\*

Weight/Gallon.....6.7 lbs  
 Solids.....40%  
 Color.....Brown

#### CONTAINER SIZES

North America: 5 gal. pail\*, 55 gal. drum, and bulk.  
 Global Zones: 5 gal. pail\*, 55 gal. drum.

20100104

\* One gallon containers available upon request.

\*\* Typical Properties; not sales specifications.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty either expressed or implied, is made or intended. Use by customer should be based upon its own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.



Performance Additives  
 Department  
 Huntington, WV 25721  
 Tel: 304-525-5171  
 Fax: 304-525-2921

U.S. Marketing Division  
 Raybo Chemical Company  
 Huntington, WV 25721  
 Tel: 304-525-5172  
 Fax: 304-525-2921



Exclusive Export  
 Management Company  
 W.R. Magnus, Inc.  
 Tel.: 301-263-6124  
 Email: rwmagnus@cocexport.com



Global Dist Zones:  
 Representatives in  
 31 Countries