



TECHNICAL BULLETIN

Raybo Chemical Company

TELEPHONE: 304-525-5171

RAYBO 61 AquaWet

Eliminates Fisheyes, Craters, and Crawling

REFERENCE	FEATURES	SYSTEM	COMMENTS	USAGE (%)	REFERENCE
	Eliminates Fisheyes, Craters and Crawling	Water and Water Reducible	Can be used for Dispersion	0.3-1% of Total Weight	

PERFORMANCE

RAYBO 61 effectively eliminates fisheyes, craters, and crawling in water and water reducible systems. It also reduces water sensitivity during the first 24 to 36 hours of the coating cure period.

RAYBO 61 is active at the coating/substrate interface.

The superior wetting capabilities of RAYBO 61 also permit its use as a dispersant. When used for this purpose it is applicable to both organic and inorganic pigments. Its use can reduce mill time, eliminate puffy structures and control flocculation.

ADVANTAGES

- Superior wetting capability
- Reduces water sensitivity during cure
- Solids listed with USDA

RECOMMENDATIONS For Surface Defects – 0.3-1% of Total Weight
 Post addition is recommended
 For Dispersion – 1-2% of Total Pigment Weight

PHYSICAL DATA**
 Weight/Gallon7.1 lbs
 Active Solids.....60%
 Appearance.....Amber Liquid

CONTAINER SIZES North America: 5 gal. pail*, 55 gal. drum, and bulk.
 Global Zones: 5 gal. pail*, 55 gal. drum.

20100104

* One gallon containers available upon request.

** Typical Properties; not sales specifications.

The information and data stated herein, although in no way guaranteed, are based upon tests and reports considered to be reliable and are believed to be accurate. No warranty either expressed or implied, is made or intended. Use by customer should be based upon its own investigations and appraisals. Any recommendation should not be construed as an invitation to use a material in infringement of patents.

